

Enhanced Single-Mode Optical Fiber (ESMF)

Improved performance across the entire 1260 nm to 1625 nm wavelength spectrum

Product Type: G.652.D

Coating Type: ColorLock-XS and Natural

Issue date: 08/10

Supersedes: 05/09

Optical Specifications

Attenuation	
Attenuation at 1310 nm	0.33 – 0.35 dB/km
Attenuation at 1383 nm*	0.32 – 0.35 dB/km
Attenuation at 1460 nm	0.25 dB/km
Attenuation at 1550 nm	0.19 – 0.21 dB/km
Attenuation at 1625 nm	0.20 – 0.23 dB/km

* Including H2-aging according to IEC 60793-2-50, type B.1.3

Other values available on request

Attenuation vs. Wavelength

Maximum attenuation change over the window from reference

Wavelength range (nm)	Reference λ (nm)	(dB/km)
1285 – 1330	1310	≤ 0.03
1525 – 1575	1550	≤ 0.02
1460 – 1625	1550	≤ 0.04

Point discontinuities

No point discontinuity greater than 0.05 dB at 1310 nm and 1550 nm.

Attenuation with Bending

Number of Turns	Mandrel Radius (mm)	Wavelength (nm)	Induced Attenuation (dB)
100	25	1310	≤ 0.05
100	25	1550	≤ 0.05
100	30	1625	≤ 0.05

Cutoff Wavelength

Cable Cutoff wavelength (Accf) ≤ 1260 nm

Mode Field Diameter

Wavelength (nm)	MFD (μm)
1310	9.0 ± 0.4
1550	10.1 ± 0.5

Chromatic Dispersion

Wavelength (nm)	Chromatic Dispersion (ps/[nm.km])
1285 – 1330	$\leq 3 $
1550	≤ 18.0
1625	≤ 22.0

Zero Dispersion Wavelength (λ_0): 1300 - 1322 nm

Slope (S_0) at λ_0 : ≤ 0.090 ps/(nm².km)

Polarization Mode Dispersion (PMD)

PMD Link Design Value** (ps $\sqrt{\text{km}}$)	≤ 0.06
Max. Individual Fiber (ps $\sqrt{\text{km}}$)	≤ 0.1

** According to IEC 60794 –3, Ed 3 (Q=0.01%)

Geometrical Specifications

Glass Geometry

Cladding Diameter	125.0 ± 0.7 μm
Core/Cladding Concentricity Error	≤ 0.5 μm
Cladding Non-Circularity	≤ 0.7 %
Fiber Curl (Radius)	≥ 4 m

Coating Geometry

Coating Diameter	242 ± 7 μm
Coating/Cladding Concentricity Error	≤ 12 μm
Coating Non-Circularity	≤ 5 %
Length	Standard lengths up to 50.4 km

Mechanical Specifications

Proof Test

The entire length is subjected to a tensile proof stress ≥ 0.7 GPa (100 kpsi); 1% strain equivalent

Tensile Strength

Dynamic tensile strength (0.5 meter gauge length):

Aged*** and unaged: median > 3.8 GPa (550 kpsi)

*** Aging at 85°C, 85% RH, 30 days

Dynamic and Static Fatigue

Dynamic fatigue, unaged and aged*** $n_d \geq 20$

Static fatigue, aged*** $n_s \geq 23$

Coating Performance

Coating strip force unaged and aged****:

- Average strip force: 1 N to 3 N

- Peak strip force: 1.2 N to 8.9 N

**** Aging:

- 0°C and 45°C
- 30 days at 85°C and 85% RH
- 14 days water immersion at 23°C
- Wasp spray exposure (Telcordia)

Environmental Specifications

Attenuation

Environmental Test	Test Conditions	Induced Attenuation at 1310, 1550 nm (dB/km)
Temperature cycling	- 60°C to 85°C	≤ 0.05
Temperature-Humidity cycling	- 10°C to 85°C, 4-98% RH	≤ 0.05
Water Immersion	14 days; 23°C	≤ 0.05
Dry Heat	30 days; 85°C	≤ 0.05
Damp Heat	30 days; 85°C; 85% RH	≤ 0.05

Typical Values

Miscellaneous

Nominal Zero Dispersion Slope	0.085 ps/(nm ² .km)
Effective group index @ 1310 nm	1.467
Effective group index @ 1550 nm	1.468
Effective group index @ 1625 nm	1.468

Rayleigh Backscatter Coefficient for 1 ns pulse width:

@ 1310 nm	- 79.4 dB
@ 1550 nm	- 81.7 dB
@ 1625 nm	- 82.5 dB

Median Dynamic Tensile Strength 5.3 GPa (750 kpsi)

(Aged at 85°C, 85% RH, 30 days; 0.5 m gauge length)